

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
14 October 2004 (14.10.2004)

PCT

(10) International Publication Number  
**WO 2004/087602 A1**

(51) International Patent Classification<sup>7</sup>: **C04B 24/26**,  
24/32

83308 Trostberg (DE). **SCHOLZ, Christian** [DE/DE];  
Dr.-Albert-Frank-Strasse 32, 83308 Trostberg (DE).

(21) International Application Number:  
PCT/EP2004/002254

(74) Common Representative: **CONSTRUCTION RE-  
SEARCH & TECHNOLOGY GMBH**; Patente, Marken,  
Dr. Albert-Frank-Strasse 32, 83308 Trostberg (DE).

(22) International Filing Date: 5 March 2004 (05.03.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
2003-100709 3 April 2003 (03.04.2003) JP

(81) Designated States (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,  
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,  
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,  
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,  
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,  
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,  
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,  
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,  
ZW.

(71) Applicant (for all designated States except US):  
**CONSTRUCTION RESEARCH & TECHNOL-  
OGY GMBH** [DE/DE]; Patente, Marken, Dr. Al-  
bert-Frank-Strasse 32, 83308 Trostberg (DE).

(84) Designated States (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,  
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), Euro-  
pean (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR,  
GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK,  
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,  
ML, MR, NE, SN, TD, TG).

(72) Inventors; and


(75) Inventors/Applicants (for US only): **MATSUMOTO**,  
Toshimi [JP/JP]; c/o Chuo-Kenkyusho, NMB Ltd., 2722  
Hagizono, Chigasaki-shi, Kanagawa-Ken (JP). **ASMUS**,  
Sven [DE/JP]; c/o Chuo-Kenkyusho, NMB Ltd., 2722  
Hagizono, Chigasaki-shi, Kanagawa-Ken (JP). **GER-  
HARD**, Albrecht [DE/DE]; Dr.-Albert-Frank-Strasse  
32, 83308 Trostberg (DE). **LORENZ**, Klaus [DE/DE];  
Dr.-Albert-Frank-Strasse 32, 83308 Trostberg (DE).  
**WAGNER**, Petra [DE/DE]; Dr.-Albert-Frank-Strasse 32,

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: CEMENT ADDITIVE



having 1 to 4 carbon atoms or arylene having 6 to 9 carbon atoms; n is 0 or 1; S<sub>1</sub> and S<sub>2</sub> are, independently of one another, -OC<sub>k</sub>H<sub>2k</sub>- or -OCH<sub>2</sub>CHR<sub>3</sub>-, with the proviso that k is 2 or 3, R<sub>3</sub> is an alkyl group having 1 to 9 carbon atoms, an aryl group having 6 to 9 carbon atoms; and 6 < m<sub>1</sub> + m<sub>2</sub> < 25.

(57) Abstract: The present invention concerns a cement ad-  
ditive containing copolymers comprising one or more con-  
stitutional units represented by formula A: (A) R<sub>1</sub> is hydro-  
gen, an alkyl group having 1 to 4 carbon atoms, an alkenyl  
group having 1 to 4 carbon atoms or an aryl group having 6  
to 9 carbon atoms; R<sub>2</sub> is hydrogen or an alkyl group having  
1 to 9 carbon atoms, an alkenyl group having 1 to 9 car-  
bon atoms or an aryl group having 6 to 9 carbon atoms; T  
is alkylene (including straight-chain and branched alkylene)

**CEMENT ADDITIVE****Description****TECHNICAL FIELD OF THE INVENTION**

The present invention relates to all types of concrete admixtures used with the aim of improving the workability of cement compositions.

(0002)

**BACKGROUND ART**

Water reducing agents are widely used with the aim of improving the quality of cement compositions such as concrete, mortar, etc. Naphthalenesulfonate-formalin condensates, melaminesulfonate-formalin condensates, ligninsulfonates, polycarboxylic acids, etc. are generally used as water reducing agents. Among these, the demand for polycarboxylic acid type water reducing agents, developed in recent years, is continually increasing because they have better water reducing properties than other water reducing agents.

(0003)

When looking at developments up to this day, polycarboxylic acid type water reducing agents can be roughly divided into dispersion type water reducing agents which aim at the water reducing effect and slump maintaining type water reducing agents which aim at preventing slump loss.

In the early days of polycarboxylic acid type water reducing agent development, when the attention was on the dispersion type water reducing agents, the use of copolymers of unsaturated dicarboxylic acids or unsaturated monocarboxylic acids not having a polyalkylene-oxide group etc. has been proposed (refer for example to Documents 1 and 2). However, the slump loss preventing properties of these agents are of course insufficient, and even their water reducing properties are inadequate. Thereafter, polycarboxylic acid type water reducing agents for cement which have a polyalkylene oxide group and improved water reducing properties such as copolymers of polyethylene glycol methacrylate and methacrylic acid (refer for example to Document 3) and copolymers of polyethylene glycol methacrylate, methacrylic acid and amide compound adducts having polyalkylene oxides of unsaturated carboxylic acid (refer for example to Document 4) etc. were developed and widely used instead of those mentioned above. However, even though these dispersion type polycarboxylic acid water reducing agents for cement have better water reducing properties than the previous water re-

ducing agents without a polyalkylene oxide group, their slump loss preventing effect is still not adequate.

(0004)

On the other hand, together with progress in concrete technology, the requirements for the slump loss preventing effect in concrete also increased and the development of the slump maintaining type of polycarboxylic acids progressed. E.g., copolymers of polyethylene glycol methacrylate and methacrylic acid (refer for example to Document 5); copolymers selected from polyalkylene glycol diester monomers having unsaturated bonds, acrylate monomers and polyalkylene glycol monoester monomers having unsaturated bonds (refer for example to Document 6); copolymers of methacrylic acid and polyethylene glycol methacrylate whose oxyethylene group has 1 to 10 and 11 to 100 different chain lengths (refer for example to Document 7); copolymers of polyoxyalkylene derivatives and maleic anhydrides (refer for example to Document 8); copolymers of polyoxyalkylene derivatives and maleic anhydrides (refer for example to Document 9); copolymers of alkenyl ethers and maleic anhydrides (refer for example to Document 10); copolymers of olefins having 2 to 8 carbon atoms and ethylenic unsaturated dicarboxylic acid anhydrides (refer for example to Document 11) and metal complexes of copolymers etc. of olefins having 2 to 8 carbon atoms and ethylenic unsaturated dicarboxylic acids and of polyacrylic acids (refer for example to Document 12) etc. have been proposed; and the slump loss preventing effect, which is insufficient with dispersion type water reducing agents, has been improved by using slump maintaining agents in combination with the dispersion type polycarboxylic acid water reducing agents mentioned above (refer for example to Document 13).

(0005)

Many inventions, like those mentioned above, are effective for improving water reducing properties, dispersion properties and slump loss preventing properties by means of polycarboxylic acid water reducing agents.

Nowadays, however, attention at concrete work site is not focused on single properties such as water reducing properties, dispersion properties or slump maintaining properties; but what, in the end, is urgently needed is a cement additive for achieving excellent working properties and workability and for realizing excellent economical efficiency during the whole work process.

Development at present, however, has stopped at improving specific properties of cement compositions.

(0006)

Document 1: JP-B-02-16264

Document 2: JP-B-03-36774

Document 3: JP-B-59-18338

Document 4: JP-B-02-7897

Document 5: JP-B-06-104585

Document 6: JP-A-05-238795

(0007)

Document 7: JP-A-09-286645

Document 8: Japanese Patent No. 2541218

Document 9: JP-A-07-215746

Document 10: JP-A-05-310458

Document 11: Japanese Patent No. 2933994

Document 12: JP-A-62-83344

Document 13: Japanese Patent No. 2741631

(0008)

#### PROBLEMS TO BE SOLVED BY THE INVENTION

Consequently, it is an object of the present invention to solve the problems of the prior art and to provide a cement additive for achieving excellent working properties and workability and for simultaneously fulfilling requirements of water reducing properties, dispersion properties and slump maintaining properties at a high level.


(0009)

#### MEANS FOR SOLVING THE PROBLEM

As a result of extensive research to solve the above-mentioned problems, the inventors of the present invention, considering that it is indispensable to simultaneously fulfill, at a high level, requirements of water reducing properties, dispersion properties and slump maintaining properties in order to achieve a superior and stable workability, found that, independent of variations in the handling conditions such as concrete temperature, water/cement ratio etc., high water reducing properties, excellent dispersion properties and very high mixing speeds, excellent flow properties and slump preventing effect can be achieved in a stable manner through the whole process from mixing to placing by using copolymers comprising specific constitutional units, and then have completed the invention.

(0010)

Therefore, the present invention relates to a cement additive containing copolymers comprising one or more constitutional units represented by formula A:



wherein

$\text{R}_1$  is hydrogen, an alkyl group having 1 to 4 carbon atoms, an alkenyl group having 1 to 4 carbon atoms or an aryl group having 6 to 9 carbon atoms;

$\text{R}_2$  is hydrogen or an alkyl group having 1 to 9 carbon atoms, an alkenyl group having 1 to 9 carbon atoms or an aryl group having 6 to 9 carbon atoms;

T is alkylene (straight-chain and branched alkylene) having 1 to 4 carbon atoms or arylene having 6 to 9 carbon atoms;


n is 0 or 1;

$\text{S}_1$  and  $\text{S}_2$  are, independently of one another,  $-\text{OC}_k\text{H}_{2k}-$  or  $-\text{OCH}_2\text{CHR}_3-$ , with the proviso that k is 2 or 3,  $\text{R}_3$  is an alkyl group having 1 to 9 carbon atoms, an aryl group having 6 to 9 carbon atoms; and

$$6 \leq m_1 + m_2 \leq 25;$$

(0011)

one or more constitutional units represented by formula B:



wherein

$\text{R}_4$  is hydrogen or a methyl group;

$\text{R}_5$  is hydrogen or a group represented by  $\text{COOY}$ ;

Y is hydrogen, an aliphatic hydrocarbon group (including straight-chain, branched, saturated and unsaturated groups) having 1 to 8 carbon atoms, a cyclic hydrocarbon group (including straight-chain, branched, saturated and unsaturated groups) having 3 to 8 carbon atoms, a hydroxyalkyl group (including branched groups) having 2 to 5 carbon atoms, a hydroxyalkenyl group having 2 to 5 carbon atoms, metal (oxidation number I or II), an ammonium group derived from alkylamine having 1 to 20 carbon atoms, alkanolamine having 1 to 20 carbon atoms, cycloalkylamine having 5 to 8 carbon atoms, arylamine having 6 to 14 carbon atoms;


A is oxygen or  $\text{NR}_6$ ; and

$R_6$  is hydrogen, an alkyl group having 1 to 20 carbon atoms, an aryl group having 6 to 20 carbon atoms, a sulfonyl group or a sulfanyl group;

and

(0012)

one or more constitutional units represented by formula C:



wherein

$R_4$ ,  $R_5$  and  $A$  have the same meaning as in formula B;

$X$  is an aliphatic hydrocarbon group (including straight-chain, branched, saturated and unsaturated groups) having 1 to 8 carbon atoms, a cyclic hydrocarbon group (including straight-chain, branched, saturated and unsaturated groups) having 3 to 8 carbon atoms, a hydroxyalkyl group (including branched groups) having 2 to 5 carbon atoms, a hydroxyalkenyl group having 2 to 5 carbon atoms, metal (oxidation number I or II), an ammonium group derived from alkylamine having 1 to 20 carbon atoms, alkanolamine having 1 to 20 carbon atoms, cycloalkylamine having 5 to 8 carbon atoms, arylamine having 6 to 14 carbon atoms.

(0013)

The present invention further relates to the before-mentioned cement additive wherein the average molecular weight of the copolymers is 5,000 to 50,000.

(0014)

The present invention also relates to the before-mentioned cement additive comprising copolymers wherein the mole ratio of the constitutional units  $A$  and  $C$  is  $A/C \geq 0.1$  and the mole ratio of the constitutional units  $B$  and  $C$  is  $B/C \leq 20$ .

The present invention further relates to the before-mentioned cement additive having slump retaining properties and comprising copolymers wherein the mole ratio of the constitutional units  $A$  and  $C$  is  $0.1 \leq A/C \leq 1$  and the mole ratio of the constitutional units  $B$  and  $C$  is  $B/C \leq 1$ .

(0015)

The present invention also relates to the before-mentioned cement additive having dispersing properties and comprising copolymers wherein the mole ratio of the constitutional units A and C is  $A/C > 1$  and the mole ratio of the constitutional units B and C is  $1 < B/C \leq 20$ .

The present invention further relates to the before-mentioned cement additive comprising copolymers wherein the mole ratio of the constitutional units A and C is  $0.1 \leq A/C \leq 1$  and the mole ratio of the constitutional units B and C is  $B/C \leq 1$ , and copolymers wherein the mole ratio of the constitutional units A and C is  $A/C > 1$  and the mole ratio of the constitutional units B and C is  $1 < B/C \leq 20$ .

(0016)

The present invention also relates to the before-mentioned cement additive comprising copolymers wherein the mole ratio of the constitutional units A and C is  $0.1 \leq A/C \leq 1$  and the mole ratio of the constitutional units B and C is  $B/C \leq 1$ , and copolymers wherein the mole ratio of the constitutional units A and C is  $A/C > 1$  and the mole ratio of the constitutional units B and C is  $1 < B/C \leq 20$  in a ratio of 20:80 to 99:1.

The present invention further relates to the before-mentioned cement additive further comprising one or more of additive I selected from the group consisting of polycarboxylic acid type copolymers comprising vinyl alcohol; polycarboxylic acid type copolymers; copolymers of alkyl vinyl ether and acrylic acid derivatives; copolymers of hydroxyalkyl vinyl ether and acrylic acid derivatives; copolymers of vinyl alcohol derivatives and acrylic acid derivatives; copolymers of vinyl ether, acrylic acid and maleic acid; copolymers of allyl ether and maleic anhydride; copolymers of allyl ether, maleic anhydride and maleic acid ether; copolymers of methacrylate alkylene oxide ether and methacrylic acid; copolymers of methacrylate alkylene oxide ether and acrylic acid; maleic acid esters; copolymers of maleic acid and styrene; ligninsulfonic acid; polymelaminesulfonic acid; bis-naphthalenesulfonic acid and gluconic acid.

(0017)

The present invention also relates to the before-mentioned cement additive comprising cement additive I and copolymers wherein the mole ratio of the constitutional units A and C is  $0.1 \leq A/C \leq 1$  and the mole ratio of the constitutional units B and C is  $B/C \leq 1$ ; wherein cement additive I is comprised in a ratio of 1 to 60 wt% of the total amount of cement additives.

The present invention further relates to the before-mentioned cement additive comprising cement additive I and copolymers wherein the mole ratio of the constitutional units A

and C is  $A/C > 1$  and the mole ratio of the constitutional units B and C is  $1 < B/C \leq 20$ ; wherein cement additive I is 50 wt% or more of the total amount of cement additives.

The present invention also relates to the before-mentioned cement additive comprising cement additive I, copolymers wherein the mole ratio of the constitutional units A and C is  $0.1 \leq A/C \leq 1$  and the mole ratio of the constitutional units B and C is  $B/C \leq 1$ , and copolymers wherein the mole ratio of the constitutional units A and C is  $A/C > 1$  and the mole ratio of the constitutional units B and C is  $1 < B/C \leq 20$ ; wherein cement additive I is comprised in a ratio of 1 to 99 wt% of the total amount of cement additives.

(0018)

The present invention further relates to the before-mentioned cement additive further comprising one or more of cement additive II selected from the group consisting of gluconic acid, sodium gluconate, saccharides, sugar alcohols, lignin, polycarboxylic acid, polyamide, polyamine, polyethoxyethylene, triethanolamine, commonly used air-entraining agents, polysaccharide derivatives, lignin derivatives, dry shrinkage reducing agents, accelerators, retarding agents, foaming agents, defoaming agents, rust preventing agents, quick setting agents, thickeners and water-soluble high molecular substances.

The present invention also relates to the before-mentioned cement additive wherein cement additive II is 40 wt% or less of the total amount of cement additives.

(0019)

The cement additive according to the present invention, by using copolymers constituted by specific constitutional units, provides excellent water reducing properties, dispersion properties and slump preventing properties and realizes excellent working properties and workability.

By further comprising two or more types of specific constitutional units at a specific ratio, the cement additive according to the present invention simultaneously and reliably provides dispersion properties and slump maintaining properties.

(0020)

The effect of different types of copolymers on the properties of concrete is generally explained by the DLVO theory and by the steric repulsion theory. Based on these theories, ideas have been proposed that specialize for example on the improvement of slump loss preventing properties by mixing copolymers with excellent dispersion properties with two or more types of copolymers with excellent slump maintaining properties. Developing these ideas still further, the present invention, based on the copolymer structure, the elements constituting said copolymers and the intramolecular ratios of the constitutional elements as well



as on the mixing ratios of the specific copolymers by which these properties can be achieved, provides excellent water reducing properties, dispersion properties and slump maintaining properties and achieves excellent working properties and workability for a wide range of concrete manufacturing conditions.

(0021)

Moreover, the cement additive according to the present invention, due to its excellent adaptability, can achieve excellent properties not only in general building construction applications but also in ultrahigh strength concrete applications, spray concrete applications and concrete products (including medium/high flow concrete products, ultra high strength concrete products, heat-cured concrete products, centrifugally cast concrete products etc.).


(0022)

#### DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

The copolymers used in the present invention are constituted by the constitutional units represented by formulae A, B and C below as indispensable units.

(0023)

Formula A is



with the proviso that

$\text{R}_1$  is hydrogen, an alkyl group having 1 to 4 carbon atoms such as methyl, etc., an alkenyl group having 1 to 4 carbon atoms such as allyl, or an aryl group having 6 to 9 carbon atoms;

$\text{R}_2$  is hydrogen or an alkyl group having 1 to 9 carbon atoms, an alkenyl group having 1 to 9 carbon atoms or an aryl group having 6 to 9 carbon atoms;

T is alkylene (straight-chain and branched alkylene) having 1 to 4 carbon atoms such as methylene, ethylene, propylene, butylene, etc., or arylene having 6 to 9 carbon atoms;


n is 0 or 1;

$\text{S}_1$  and  $\text{S}_2$  are, independently of one another,  $-\text{OC}_k\text{H}_{2k}-$  or  $-\text{OCH}_2\text{CHR}_3-$ , with the proviso that k is 2 or 3,  $\text{R}_3$  is an alkyl group having 1 to 9 carbon atoms, an aryl group having 6 to 9 carbon atoms; and

$$6 \leq m_1 + m_2 \leq 25.$$

(0024)

Formula B is



with the proviso that

R<sub>4</sub> is hydrogen or a methyl group;

R<sub>5</sub> is hydrogen or a group represented by COOY;


Y is hydrogen, an aliphatic hydrocarbon group (including straight-chain, branched, saturated or unsaturated groups) having 1 to 8 carbon atoms, a cyclic hydrocarbon group (including straight-chain, branched, saturated or unsaturated groups) having 3 to 8 carbon atoms, a hydroxyalkyl group (including branched groups) having 2 to 5 carbon atoms, a hydroxyalkenyl group having 2 to 5 carbon atoms, metal (oxidation number I or II), an ammonium group derived from alkylamine having 1 to 20 carbon atoms, alkanolamine having 1 to 20 carbon atoms, cycloalkylamine having 5 to 8 carbon atoms, arylamine having 6 to 14 carbon atoms;

A is oxygen or NR<sub>6</sub>; and

R<sub>6</sub> is hydrogen, an alkyl group having 1 to 20 carbon atoms, an aryl group having 6 to 20 carbon atoms, a sulfonyl group or a sulfanyl group.

(0025)

Formula C is



with the proviso that

R<sub>4</sub>, R<sub>5</sub> and A have the same meaning as in formula B;

X is an aliphatic hydrocarbon group (including straight-chain, branched, saturated and unsaturated groups) having 1 to 8 carbon atoms, a cyclic hydrocarbon group (including straight-chain, branched, saturated and unsaturated groups) having 3 to 8 carbon atoms, a hydroxyalkyl group (including branched groups) having 2 to 5 carbon atoms, a hydroxyalkenyl group having 2 to 5 carbon atoms, metal (oxidation number I or II), an ammonium group de-

rived from alkylamine having 1 to 20 carbon atoms, alkanolamine having 1 to 20 carbon atoms, cycloalkylamine having 5 to 8 carbon atoms, arylamine having 6 to 14 carbon atoms.  
(0026)

Moreover, in the present invention, these copolymers can include, as constitutional unit, one or more types of monomer selected from among monomers that can be copolymerized with the constitutional units A, B and C, in a range in which the desired properties are not lost.

Example of monomers that can be copolymerized include unsaturated monocarboxylic acid derivatives such as polyethylene glycol mono(meth)acrylate, polypropylene glycol (meth)acrylate, polybutylene glycol (meth)acrylate, polyethylene glycol polypropylene glycol mono(meth)acrylate, polyethylene glycol polybutylene glycol mono(meth)acrylate, polypropylene glycol polybutylene glycol mono(meth)acrylate, polyethylene glycol polypropylene glycol polybutylene glycol mono(meth)acrylate, methoxypolyethylene glycol mono(meth)acrylate, methoxypolypropylene glycol mono(meth)acrylate, methoxypolybutylene glycol mono(meth)acrylate, methoxypolyethylene glycol polypropylene glycol mono(meth)acrylate, methoxypolyethylene glycol polybutylene glycol mono(meth)acrylate, methoxypolypropylene glycol polybutylene glycol mono(meth)acrylate, methoxypolyethylene glycol polypropylene glycol polybutylene glycol mono(meth)acrylate, ethoxypolyethylene glycol mono(meth)acrylate, ethoxypolypropylene glycol mono(meth)acrylate, ethoxypolybutylene glycol mono(meth)acrylate, ethoxypolyethylene glycol polypropylene glycol mono(meth)acrylate, ethoxypolyethylene glycol polybutylene glycol mono(meth)acrylate, ethoxypolypropylene glycol polybutylene glycol mono(meth)acrylate, ethoxypolyethylene glycol polypropylene glycol polybutylene glycol mono(meth)acrylate, etc.;

(0027)

allyl alcohol acid derivatives such as polyethylene glycol mono(meth)allyl ether, polypropylene glycol mono(meth)allyl ether, polybutylene glycol mono(meth)allyl ether, polyethylene glycol polypropylene glycol mono(meth)allyl ether, polyethylene glycol polybutylene glycol mono(meth)allyl ether, polypropylene glycol polybutylene glycol mono(meth)allyl ether, polyethylene glycol polypropylene glycol polybutylene glycol mono(meth)allyl ether, methoxypolyethylene glycol mono(meth)allyl ether, methoxypolypropylene glycol mono(meth)allyl ether, methoxypolybutylene glycol mono(meth)allyl ether, methoxypolyethylene glycol polypropylene glycol mono(meth)allyl ether, methoxypolyethylene glycol polybutylene glycol mono(meth)allyl ether, methoxypolypropylene glycol polybutylene glycol

mono(meth)allyl ether, methoxypolyethylene glycol polypropylene glycol polybutylene glycol mono(meth)allyl ether, ethoxypolyethylene glycol mono(meth)allyl ether, ethoxypolypropylene glycol mono(meth)allyl ether, ethoxypolybutylene glycol mono(meth)allyl ether, ethoxypolyethylene glycol polypropylene glycol mono(meth)allyl ether, ethoxypolyethylene glycol polybutylene glycol mono(meth)allyl ether, ethoxypolypropylene glycol polybutylene glycol mono(meth)allyl ether, etc.;

(0028)

crotyl alcohol acid derivatives such as

polyethylene glycol mono(metha)crotyl ether, polypropylene glycol mono(metha)crotyl ether, polybutylene glycol mono(metha)crotyl ether, polyethylene glycol polypropylene glycol mono(metha)crotyl ether, polyethylene glycol polybutylene glycol mono(metha)crotyl ether, polypropylene glycol polybutylene glycol mono(metha)crotyl ether, polyethylene glycol polypropylene glycol polybutylene glycol mono(metha)crotyl ether, methoxypolyethylene glycol mono(metha)crotyl ether, methoxypolypropylene glycol mono(metha)crotyl ether, methoxypolybutylene glycol mono(metha)crotyl ether, methoxypolyethylene glycol polypropylene glycol mono(metha)crotyl ether, methoxypolyethylene glycol polybutylene glycol mono(metha)crotyl ether, methoxypolypropylene glycol polybutylene glycol mono(metha)crotyl ether, methoxypolyethylene glycol polypropylene glycol polybutylene glycol mono(metha)crotyl ether, ethoxypolyethylene glycol mono(metha)crotyl ether, ethoxypolypropylene glycol mono(metha)crotyl ether, ethoxypolybutylene glycol mono(metha)crotyl ether, ethoxypolyethylene glycol polypropylene glycol mono(metha)crotyl ether, ethoxypolyethylene glycol polybutylene glycol mono(metha)crotyl ether, ethoxypolypropylene glycol polybutylene glycol mono(metha)crotyl ether, ethoxypolyethylene glycol polypropylene glycol polybutylene glycol mono(metha)crotyl ether, etc.;

(0029)

diesters of unsaturated dicarboxylic acids such as maleic acid, fumaric acid, citraconic acid, etc. and aliphatic alcohols having 1 to 20 carbon atoms or glycol having 2 to 4 carbon atoms or polyalkylene glycol having 2 to 100 mols of these glycols; aromatic vinyls such as styrene etc.; unsaturated sulfonic acids such as (meth)allyl sulfonic acid, sulfoethyl (meth)acrylate, 2-methylpropane sulfonic acid (meth)acrylamide, styrene sulfonic acid and their monovalent salts, divalent salts, ammonium salts and organic amine salts; unsaturated hydrocarbons having 2 to 20 carbon atoms such as ethylene, propylene, 1-butene, 2-butene, isobutylene, n-pentene, isoprene, 2-methyl-1-butene, n-hexane, 2-methyl-1-pentene, 3-methyl-1-pentene, 4-

methyl-1-pentene, 2-ethyl-1-butene, diisobutylene, 1,3-butadiene, 1,3-hexadiene, 1,3-octadiene, 2-methyl-4-dimethyl-1-pentene, 2-methyl-4-dimethyl-2-pentene, etc.

(0030)

Constitutional unit A is used to incorporate an alkylene oxide chain or a similar structure into the copolymer structure. It can be said that the alkylene oxide chain mainly has an influence on the dispersions properties; in the present invention, the most preferred dispersion properties are obtained when  $m_1 + m_2$  from  $S_1$  and  $S_2$  of the alkylene oxide chain in constitutional unit A is 6 to 25. Moreover, the preferred molecular weight is 5,000 to 50,000.

(0031)

Preferred specific examples of constitutional unit A include polyethylene glycol monovinyl ether (molecular weight 300), polyethylene glycol monovinyl ether (molecular weight 500), polyethylene glycol monovinyl ether (molecular weight 750), polyethylene glycol monovinyl ether (molecular weight 1,000), methylpolyethylene glycol monovinyl ether (molecular weight 300), methylpolyethylene glycol monovinyl ether (molecular weight 500), methylpolyethylene glycol monovinyl ether (molecular weight 750), methylpolyethylene glycol monovinyl ether (molecular weight 1,000), etc.

(0032)

It can be considered that the structure and the amount of constitutional unit B mainly have an influence on the slump maintaining properties of cement compositions. It is possible to obtain copolymers for achieving excellent slump maintaining properties by incorporating constitutional unit B having a suitable structure at a specific amount into the structure of the copolymer.

Preferred specific examples of constitutional unit B include methacrylic acid, maleic acid anhydride, maleic acid, acrylic acid, etc.

(0033)

It can be considered that, in the copolymers, constitutional unit C has the role of maintaining the cement composition in a good state. This constitutional unit, which plays a very important role for achieving excellent workability, keeps the cement and the aggregates well blended and maintains an appropriate degree of viscosity and flow properties even if the water/cement ratio in the cement composition and the temperature change and time passes, and is one of the most characteristic features of the present invention.

Preferred specific examples of constitutional unit C include methyl (meth)acrylate, ethyl (meth)acrylate, isobutyl (meth)acrylate, n-butyl (meth)acrylate, hydroxypropyl (meth)acrylate, hydroxyethyl (meth)acrylate, maleic acid dibutyl ester, methyl (meth)acrylate.

Constitutional units A, B and C are important elements in that each shows a different effect in the copolymers.

Thus, the three constitutional units are indispensable.

(0034)

In the copolymers used in the present invention, it is preferred that the mole ratio of the constitutional units A and C is  $A/C \geq 0.1$  and the mole ratio of the constitutional units B and C is  $B/C \leq 20$ .

Among these, copolymers wherein the mole ratio of the constitutional units A and C is  $0.1 \leq A/C \leq 1$  and the mole ratio of the constitutional units B and C is  $B/C \leq 1$  are preferably used as slump maintaining agents because, when used as cement additive, they have slump maintaining properties.

Moreover, copolymers wherein the mole ratio of the constitutional units A and C is  $A/C > 1$  and the mole ratio of the constitutional units B and C is  $1 < B/C \leq 20$  are preferably used as dispersing agents because, when used as cement additive, they have dispersion properties.

(0035)

Consequently, by using a cement additive comprising both copolymers wherein the mole ratio of the constitutional units A and C is  $0.1 \leq A/C \leq 1$  and the mole ratio of the constitutional units B and C is  $B/C \leq 1$ , and copolymers wherein the mole ratio of the constitutional units A and C is  $A/C > 1$  and the mole ratio of the constitutional units B and C is  $1 < B/C \leq 20$  it is possible to simultaneously and reliably achieve slump maintaining properties and dispersion properties.

In this case it is preferred to include copolymers wherein the mole ratio of the constitutional units A and C is  $0.1 \leq A/C \leq 1$  and the mole ratio of the constitutional units B and C is  $B/C \leq 1$ , and copolymers wherein the mole ratio of the constitutional units A and C is  $A/C > 1$  and the mole ratio of the constitutional units B and C is  $1 < B/C \leq 20$  in a ratio of 20:80 to 99:1; while a ratio of 50:50 to 80:20 is even more preferred.

(0036)

The cement additive according to the present invention may further include one or more of additive I selected from the group consisting of polycarboxylic acid type copolymers comprising vinyl alcohol; polycarboxylic acid type copolymers; copolymers of alkyl vinyl ether and acrylic acid derivatives; copolymers of hydroxyalkyl vinyl ether and acrylic acid derivatives; copolymers of vinyl alcohol derivatives and acrylic acid derivatives; copolymers of vinyl ether, acrylic acid and maleic acid; copolymers of allyl ether and maleic anhydride;

copolymers of allyl ether, maleic anhydride and maleic acid esters; copolymers of methacrylate polyalkylene oxide esters and methacrylic acid; copolymers of maleic acid esters, maleic acid and styrene; ligninsulfonic acid salts; polymelaminesulfonic acid salts; bis-naphthalenesulfonic acid salts and gluconic acid salts.

(0037)

Cement additives having the above-mentioned slump maintaining properties, when comprising cement additive I and copolymers wherein the mole ratio of the constitutional units A and C is  $0.1 \leq A/C \leq 1$  and the mole ratio of the constitutional units B and C is  $B/C \leq 1$ , preferably comprise cement additive I in a ratio of 1 to 60 wt% of the total amount of cement additives.

Cement additives having the above-mentioned dispersion properties, when comprising cement additive I and copolymers wherein the mole ratio of the constitutional units A and C is  $A/C > 1$  and the mole ratio of the constitutional units B and C is  $1 < B/C \leq 20$ , preferably comprise cement additive I in a ratio of 50 wt% or more of the total amount of cement additives.

When blended copolymers having the above-mentioned slump maintaining properties and dispersion properties are used, it is preferred to use cement additive I in a ratio of 1 to 99 wt% of the total amount of cement additives.

(0038)

The cement additive according to the present invention may further include one or more of cement additive II selected from the group consisting of gluconic acid, sodium gluconate, saccharides, sugar alcohols, lignin, polycarboxylic acid, polyamide, polyamine, polyamide polyamine, polyethoxyethylene, triethanolamine, commonly used air-entraining agents, polysaccharide derivatives, lignin derivatives, dry shrinkage reducing agents, accelerators, retarding agents, foaming agents, defoaming agents, rust preventing agents, quick setting agents, thickeners and water-soluble high molecular substances.

In this case, it is preferred to use cement additive II in a ratio of 40 wt% or less of the total amount of cement additives.

(0039)

#### Examples

Examples of the cement additive according to the present invention will be given; however, the present invention is not limited by these embodiments.

(0040)

(Synthesis)

Prescribed amounts of water and monomers for obtaining constitutional unit A were introduced into a reaction vessel equipped with a thermometer, a stirrer, a reflux condenser and two inlets. While stirring and controlling the temperature so that it normally was 30 °C or less, prescribed amounts of hydrogen peroxide, iron sulfate and 3-mercaptopropionic acid or similar polymerization catalysts were introduced.

Monomers for obtaining constitutional unit B and monomers for obtaining constitutional unit C or a mixed solution of these monomers to which one or more monomers selected from a group consisting of other monomers had been added and which had been prepared in a separate vessel at a prescribed ratio were introduced into the reaction solution at a prescribed speed.

After a prescribed reaction time, an aqueous solution of caustic soda was introduced to terminate the reaction.

The monomers and copolymers used in the present invention are shown in Tables 1 and 2 respectively.

(0041)

(Table 1)

Table 1: Copolymers and the ratio of the constitutional unit elements (monomers)

Co-polymer	Monomer					Monomer ratio (mole ratio)			
	A	B		C		A/C	B/C	B(I)/ B(II)	C(I)/ C(II)
		B(I)	B(II)	C(I)	C(II)				
P1	A-1	B-1	B-2	C-2		0.8	0.7	3.0	
P2	A-2	B-1		C-2		0.6	0.9		
P3	A-2	B-1		C-1	C-2	0.6	0.9		0.3
P4	A-2	B-1		C-3	C-2	0.4	0.6		1.0
P5	A-3	B-1		C-2		1.0	1.0		
P6	A-2	B-1		C-2		1.0	1.0		
P7	A-3	B-1		C-2		1.3	2.8		
P8	A-4	B-1	B-2	C-2		2.5	5.3	20.0	
P9	A-2	B-1		C-2		5.0	6.0		
P10	A-2	B-1		C-4		10.0	12.0		
P11	A-2	B-1		C-1		5.0	6.0		
P12	A-4	B-1	B-2	C-5		10.0	20.0	10.0	
P13	A-4	B-1	B-2	-	-			10.0	
P14	A-5	B-1	B-2	-	-			10	

(0042)



Table 2: Types of monomers

Monomer A	A-1	Monovinyl ether (molecular weight 300)
	A-2	Monovinyl ether (molecular weight 500)
	A-3	Monovinyl ether (molecular weight 750)
	A-4	Monovinyl ether (molecular weight 1,100)
	A-5	Monovinyl ether (molecular weight 5,800)
Monomer B	B-1	Acrylic acid
	B-2	Maleic acid anhydride
Monomer C	C-1	Methyl acrylate
	C-2	Hydroxypropyl acrylate
	C-3	Hydroxypropyl methacrylate
	C-4	Hydroxyethyl acrylate
	C-5	Maleic acid dibutyl ester

(0043)

The copolymers obtained and the combinations with additive I and additive II are shown in Table 3.

(Table 3)

Table 3: Mixtures

Mixture	Copolymer I	Copolymer II	Additive I	Additive II	Mixing ratio
1	P1	P8	-		30/70
2	P3	P11	P14		15/70/15
3	P6	P7			70/30
4	P5	P10			30/70
5	P5	P7	PA		50/30/20
6	P4	P6	PB		20/50/30
7	P2	P9	P12	Triethanol amine	10/25/65
8	P2	P9	P12	Gluconic acid	47/32/20/1
9	P2	P9	P12	Triethanol amine	20/15/65
10	P13	P14			15/85

PA: Polycarboxylic acid type copolymers comprising vinyl alcohol

PB: Polycarboxylic acid type copolymers

(0044)

In order to evaluate the cement additive according to the present invention, concrete was prepared with the prescribed mixtures at the concrete temperature and with the different water/cement ratios given below, and the ability of maintaining good workability was judged by comparing the difference in the state of the concrete and of the values for slump and slump flow of the concrete directly after its preparation and after having left the concrete to rest for 60 minutes.

(0045)

(Concrete mixing and mixtures)

Concrete having a target slump of  $20 \pm 1.0$  cm and a target air amount of  $4.5 \% \pm 0.5$  % at a water/cement ratio of 45 % and a target slump flow of  $45 \pm 2.5$  cm and a target air amount of  $3.0 \% \pm 0.5$  % at a water/cement ratio of 35 % was prepared with the standard mixtures according to the specifications of this company.

The concrete was prepared by weighing each material so as to obtain a mixed amount of 80 liters, introducing all the materials into a 100 liter pan-type forced mixer and mixing them for 120 seconds.

(0046)

(Materials used)

Cement: Normal Portland cement with a density of  $3.16 \text{ g/cm}^3$  of Taiheiyo Cement Corporation.

Fine aggregate: Oigawa river sand with a density of  $2.59 \text{ g/cm}^3$

Coarse aggregate: Crushed stones from Ome with a density of  $2.65 \text{ g/cm}^3$

Slump measurement: according to JIS A-1101

(0047)

(Evaluation of changes in the slump values)

The difference between the slump directly after preparing the concrete and the slump after having left the concrete to rest for 60 minutes was:

- a: less than 3.0 cm,
- b: 3.0 cm or more but less than 6.0 cm,
- c: 6.0 cm or more.

(Evaluation of changes in the slump flow values)

The difference between the slump flow directly after preparing the concrete and the slump flow after having left the concrete to rest for 60 minutes was:

- a: less than 5.0 cm,
- b: 5.0 cm or more but less than 10.0 cm,
- c: 10.0 cm or more.

(0048)

(Evaluation of changes in the state of the concrete)

Regarding concrete directly after preparation and concrete having been left to rest for 5, 15, 30 and 60 minutes, the ease of mixing, the flow properties, the cementing of mortar and

aggregate, the appearance during slumping and the shape after slumping were observed and evaluated in three grades: a, b and c.

(0049)

(Overall evaluation)

Based on the evaluation of the changes in slump, in slump flow and in the state of the concrete, the overall evaluation was made in three grades: a, b and c, and the evaluation results for the Examples are shown in Table 4.

(0050)

(Table 4)

MBJ-0525

Table 4: Evaluation results 1 of the Examples

	Mixture	Water/cement ratio (%)	Amount of additive (%)	Temperature (°C)	Slump difference	Slump flow difference	State	Overall Evaluation
Example 1	1	45	0.7	20	b	a	a	b - a
Example 2	2	45	0.85	20	b	a	a	b - a
Example 3	3	45	0.7	20	a	a	a	a
Example 4	4	45	0.85	20	b	a	a	b - a
Example 5	5	45	0.85	20	a	a	a	a
Example 6	6	45	0.8	20	b	a	a	b - a
Example 7	7	45	0.7	20	b	a	a	b - a
Example 8	8	45	1.2	30	b	b	a	b - a
Example 9	9	35	1.2	20	-	a	a	a
Comp. Ex. 1	10	45	0.6	20	b	b	b	b
Comp. Ex. 2	-	45	0.9	30	c	c	c	c
Comp. Ex. 3	-	35	1.45	20	-	c	c	c

Comparative Examples 2 and 3: Company P, polycarboxylic acid ether high performance AE water-reducing agent

Compared to the Comparative Examples, the cement additive according to the present invention simultaneously achieved dispersion properties and slump maintaining properties and good workability.

(0051)

(Mixing time)

The mixing time is the time from the start of the mixing until the end of the mixing determined by visual observation of the mixing state of the concrete.

(Table 5)

Table 5: Evaluation results 2 of the Examples


	Mixture	Water/cement ratio (%)	Amount of additive (%)	Temperature (°C)	Mixing time (sec.)
Example 10	9	45	0.95	12	11
Example 11	7	45	1.0	12	11
Example 12	9	35	0.95	12	17
Example 13	7	35	1.0	12	18
Comp. Ex. 4		45	0.9	12	18
Comp. Ex. 5		35	0.95	12	30

Comparative Examples 4 and 5: Company P, polycarboxylic acid ether high performance AE water-reducing agent

Compared with the Comparative Examples, Examples 10 and 11, which have the same water/cement ratio as Comparative Example 4, and Examples 12 and 13, which have the same water/cement ratio as Comparative Example 5, have far shorter mixing times, which makes it possible to reduce the manufacturing times of concrete.

Claims

1. A cement additive containing copolymers comprising one or more constitutional units represented by formula A:



wherein

$\text{R}_1$  is hydrogen, an alkyl group having 1 to 4 carbon atoms, an alkenyl group having 1 to 4 carbon atoms or an aryl group having 6 to 9 carbon atoms;

$\text{R}_2$  is hydrogen or an alkyl group having 1 to 9 carbon atoms, an alkenyl group having 1 to 9 carbon atoms or an aryl group having 6 to 9 carbon atoms;


T is alkylene (including straight-chain and branched alkylene) having 1 to 4 carbon atoms or arylene having 6 to 9 carbon atoms;

n is 0 or 1;

$\text{S}_1$  and  $\text{S}_2$  are, independently of one another,  $-\text{OC}_k\text{H}_{2k}-$  or  $-\text{OCH}_2\text{CHR}_3-$ , with the proviso that k is 2 or 3,  $\text{R}_3$  is an alkyl group having 1 to 9 carbon atoms, an aryl group having 6 to 9 carbon atoms; and

$$6 \leq m_1 + m_2 \leq 25;$$

one or more constitutional units represented by formula B:



wherein

$\text{R}_4$  is hydrogen or a methyl group;

$\text{R}_5$  is hydrogen or a group represented by  $\text{COOY}$ ;

Y is hydrogen, an aliphatic hydrocarbon group (including straight-chain, branched, saturated and unsaturated groups) having 1 to 8 carbon atoms, a cyclic hydrocarbon group (including straight-chain, branched, saturated and unsaturated groups) having 3 to 8 carbon atoms, a hydroxyalkyl group (including branched groups) having 2 to 5 carbon atoms, a hydroxyalkenyl group having 2 to 5 carbon atoms, metal (oxidation number I or II), an ammonium group derived from alkylamine having 1 to 20 carbon atoms, alkanolamine having 1 to


20 carbon atoms, cycloalkylamine having 5 to 8 carbon atoms, arylamine having 6 to 14 carbon atoms;

A is oxygen or  $\text{NR}_6$ ; and

$\text{R}_6$  is hydrogen, an alkyl group having 1 to 20 carbon atoms, an aryl group having 6 to 20 carbon atoms, a sulfonyl group or a sulfanyl group;

and

one or more constitutional units represented by formula C:



wherein

$\text{R}_4$ ,  $\text{R}_5$  and A have the same meaning as in formula B;

X is an aliphatic hydrocarbon group (including straight-chain, branched, saturated and unsaturated groups) having 1 to 8 carbon atoms, a cyclic hydrocarbon group (including straight-chain, branched, saturated and unsaturated groups) having 3 to 8 carbon atoms, a hydroxyalkyl group (including branched groups) having 2 to 5 carbon atoms, a hydroxyalkenyl group having 2 to 5 carbon atoms, metal (oxidation number I or II), an ammonium group derived from alkylamine having 1 to 20 carbon atoms, alkanolamine having 1 to 20 carbon atoms, cycloalkylamine having 5 to 8 carbon atoms, arylamine having 6 to 14 carbon atoms.

2. The cement additive according to claim 1 wherein the average molecular weight of the copolymers is 5,000 to 50,000.

3. The cement additive according to claims 1 or 2 comprising copolymers wherein the mole ratio of the constitutional units A and C is  $\text{A/C} \geq 0.1$  and the mole ratio of the constitutional units B and C is  $\text{B/C} \leq 20$ .

4. The cement additive according to any of claims 1 to 3 having slump retaining properties and comprising copolymers wherein the mole ratio of the constitutional units A and C is  $0.1 \leq \text{A/C} \leq 1$  and the mole ratio of the constitutional units B and C is  $\text{B/C} \leq 1$ .

5. The cement additive according to any of claims 1 to 3 having dispersing properties and comprising copolymers wherein the mole ratio of the constitutional units A and C is  $A/C > 1$  and the mole ratio of the constitutional units B and C is  $1 < B/C \leq 20$ .

6. The cement additive according to any of claims 1 to 3 comprising copolymers wherein the mole ratio of the constitutional units A and C is  $0.1 \leq A/C \leq 1$  and the mole ratio of the constitutional units B and C is  $B/C \leq 1$ , and copolymers wherein the mole ratio of the constitutional units A and C is  $A/C > 1$  and the mole ratio of the constitutional units B and C is  $1 < B/C \leq 20$ .

7. The cement additive according to claim 6 comprising copolymers wherein the mole ratio of the constitutional units A and C is  $0.1 \leq A/C \leq 1$  and the mole ratio of the constitutional units B and C is  $B/C \leq 1$ , and copolymers wherein the mole ratio of the constitutional units A and C is  $A/C > 1$  and the mole ratio of the constitutional units B and C is  $1 < B/C \leq 20$  in a ratio of 20:80 to 99:1.

8. The cement additive according to any of claims 1 to 7 further comprising one or more of additive I selected from the group consisting of polycarboxylic acid type copolymers comprising vinyl alcohol; polycarboxylic acid type copolymers; copolymers of alkyl vinyl ether and acrylic acid derivatives; copolymers of hydroxyalkyl vinyl ether and acrylic acid derivatives; copolymers of vinyl alcohol derivatives and acrylic acid derivatives; copolymers of vinyl ether, acrylic acid and maleic acid; copolymers of allyl ether and maleic anhydride; copolymers of allyl ether, maleic anhydride and maleic acid ether; copolymers of methacrylate alkylene oxide ether and methacrylic acid; copolymers of methacrylate alkylene oxide ether and acrylic acid; maleic acid esters; copolymers of maleic acid and styrene; ligninsulfonic acid; polymelaminesulfonic acid; bis-naphthalenesulfonic acid and gluconic acid.

9. The cement additive according to claim 8 comprising cement additive I and copolymers wherein the mole ratio of the constitutional units A and C is  $0.1 \leq A/C \leq 1$  and the mole ratio of the constitutional units B and C is  $B/C \leq 1$ ; wherein cement additive I is comprised in a ratio of 1 to 60 wt% of the total amount of cement additives.

10. The cement additive according to claim 8 comprising cement additive I and copolymers wherein the mole ratio of the constitutional units A and C is  $A/C > 1$  and the mole



ratio of the constitutional units B and C is  $1 < B/C \leq 20$ ; wherein cement additive I is 50 wt% or more of the total amount of cement additives.

11. The cement additive according to claim 8 comprising cement additive I, copolymers wherein the mole ratio of the constitutional units A and C is  $0.1 \leq A/C \leq 1$  and the mole ratio of the constitutional units B and C is  $B/C \leq 1$ , and copolymers wherein the mole ratio of the constitutional units A and C is  $A/C > 1$  and the mole ratio of the constitutional units B and C is  $1 < B/C \leq 20$ ; wherein cement additive I is comprised in a ratio of 1 to 99 wt% of the total amount of cement additives.

12. The cement additive according to claims 1 to 11 further comprising one or more of cement additive II selected from the group consisting of gluconic acid, sodium gluconate, saccharides, sugar alcohols, lignin, polycarboxylic acid, polyamide, polyamine, polyethoxyethylene, triethanolamine, commonly used air-entraining agents, polysaccharide derivatives, lignin derivatives, dry shrinkage reducing agents, accelerators, retarding agents, foaming agents, defoaming agents, rust preventing agents, quick setting agents, thickeners and water-soluble high molecular substances.

13. The cement additive according to claim 12 wherein cement additive II is 40 wt% or less of the total amount of cement additives.

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/EP2004/002254

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 C04B24/26 C04B24/32

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 C04B C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, CHEM ABS Data

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 02/096823 A (NIPPON CATALYTIC CHEM IND ;YAMASHITA AKIHIKO (JP); HIRATA TSUYOSHI) 5 December 2002 (2002-12-05) abstract; claim 2; examples 4-6; table 1 -----	1,8
X	EP 1 052 232 A (TAIHEIYO CEMENT CORP) 15 November 2000 (2000-11-15) examples 3,6 -----	1,2
X	WO 01/58579 A (TSUZUKI TOSHITAKA ;MIYATA AKITAKA (JP); NARUSE SHIHO (JP); NAT STA) 16 August 2001 (2001-08-16) abstract; table 1 -----	1
X	DE 199 26 611 A (SUEDEDEUTSCHE KALKSTICKSTOFF) 14 December 2000 (2000-12-14) claim 1 -----	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

27 May 2004

Date of mailing of the international search report

27. 07. 04

Name and mailing address of the ISA

European Patent Office, P.B. 6818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Pollio, M

## INTERNATIONAL SEARCH REPORT

International application No.  
PCT/EP2004/002254

### Box II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:  
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:  
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:  
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

### Box III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☒ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

1-13

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. claims: [1-13]

1.0) A cement additive containing copolymers comprising a unit of formula A, an acid unit of formula B and an acrylate unit of formula C.

---

2. claims: [1-13]

1.1) A cement additive containing copolymers comprising a unit of formula A, a maleic anhydride unit of formula B and an acrylate unit of formula C.

---

3. claims: [1-13]

1.2) A cement additive containing copolymers comprising a unit of formula A, a maleic imide unit of formula B and an acrylate unit of formula C.

---

4. claims: [1-13]

1.3) A cement additive containing copolymers comprising a unit of formula A, an acid unit or a maleic anhydride or imide unit of formula B and an acrylamide unit of formula C.

---

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP2004/002254

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 02096823	A	05-12-2002	CN 1463259 T EP 1390317 A1 WO 02096823 A1 US 2003199616 A1	24-12-2003 25-02-2004 05-12-2002 23-10-2003
EP 1052232	A	15-11-2000	JP 2000169206 A JP 2001002788 A JP 2001064070 A JP 2001064072 A CA 2318090 A1 EP 1052232 A1 US 6437027 B1 WO 0032534 A1 JP 2001097759 A JP 2001097758 A JP 2001130943 A	20-06-2000 09-01-2001 13-03-2001 13-03-2001 08-06-2000 15-11-2000 20-08-2002 08-06-2000 10-04-2001 10-04-2001 15-05-2001
WO 0158579	A	16-08-2001	JP 2001220196 A AU 3314501 A EP 1409121 A1 WO 0158579 A1 US 2003209695 A1	14-08-2001 20-08-2001 21-04-2004 16-08-2001 13-11-2003
DE 19926611	A	14-12-2000	DE 19926611 A1 AT 245173 T AU 762434 B2 AU 4394900 A CA 2375597 A1 DE 50002923 D1 DK 1189955 T3 WO 0077058 A1 EP 1189955 A1 ES 2203457 T3 HK 1044785 A1 JP 3411538 B2 JP 2000351820 A PT 1189955 T	14-12-2000 15-08-2003 26-06-2003 02-01-2001 21-12-2000 21-08-2003 10-11-2003 21-12-2000 27-03-2002 16-04-2004 07-11-2003 03-06-2003 19-12-2000 31-12-2003